

Außenstelle Erwitte · Auf den Thränen 2 · 59597 Erwitte · Telefon (02943) 897-0 · Telefax (02943) 897 33 · E-Mail: erwitte@mpanrw.de

Report of the classification of the reaction to fire performance

No. 231000720-3

issued 15.05.2020

English version

Sponsor

GRAFITYP Selfadhesive Products N.V. Centrum Zuid 1539

3530 Houthalen Belgium

Order

Classification of the reaction to fire performance according to DIN EN 13501-1:2019-05

Date of order: 12.03.2020

Identification number of the notified testing institute: 0432

Name of the classified product:

PVC-self-adhesive films "Solvent Media Polymer Series"

This report gives the classification of the above-mentioned building product in accordance to the procedure given in DIN EN 13501-1.

Publishing and copying of classification reports without permission of the MPA NRW is only allowed without any changes of the content and the form of the reports.

The shortened reproduction of classification reports needs the permission of the MPA NRW.

This classification report consists of 3 pages.



1 Description of the building product

Polymer PVC-self-adhesive films with an acrylate-based adhesive coating on the backside

Thickness of the films: 75 µm and 80 µm

Mass per unit area of the self-adhesive films: app. 112 g/m² - app. 130 g/m² Colour of the films: a) transparent, b) white, c) grey, d) beige, e) brown

Colour of the adhesive: a) transparent, b) grey

2. Test reports and test results supporting the classification

2.1 Test reports

Name of the test laboratory	Sponsor	No. of the test report	Test procedure
MPA NRW	GRAFITYP Selfadhesive Products N.V.	231000720-1 of 15.05.20 231000720-2 of 15.05.20	IV.

2.2 Test results

The following test results are the basis of the classification

		Number of tests per-	Test results	
Test method	Parameter		Average values of continously parameter	Requirements of diskrete parameter
DIN EN ISO 11925-2 30 s flaming time	Flamespread ≤150 mm Burning droplets/particles	60		yes no
	FIGRA _{0.2} in W/s	7	71	***
	FIGRA _{0.4} in W/s		6	
	THR _{600s} in MJ		1.3	
DIN EN 42022	LFS _{edge}			< edge
DIN EN 13823	SMOGRA in m²/s²	•	14	m-m
	TSP _{600s} in m ²		39	
	Duration of burning droplets/particles in s		0	



3. Classification and direct field of application

3.1 Reference

This classification was carried out in accordance to the clauses 11 and 14 of the standard DIN EN 13501-1:2010-01.

3.2 Classification

The tested building product in relation to its reaction to fire behaviour is classified as: B

The additional classification in relation to smoke production is:

The additional classification in relation to flaming droplets/particles is:

The classification of the reaction to fire performance is therefore:

Fire behaviour	Smoke devel- opment	Flaming droplets
В	s1	d0

i. e. **B - s1,d0**

3.3 Field of application of the product

The classification is valid solely for the product described in clause 1 for the application on metallic substrates of the Euroclasses A1 or A2-s1,d0 with a density of \geq 5887.5 kg/m³, a thickness of \geq 0.6 mm and a melting point of \geq 1000 °C.

4. Restrictions

This classification report does not represent type approval or certification of the product.

5. Remark

This classification report written in English language is issued additionally to the report written in German language with the same report number. In case of doubt the German version is valid solely.

Erwitte, 15.05.2020

On behalf

Dipl.-Ing. Rademacher

Head of notified testing body

MPA NRW

Dipl.-Ing. Schreiner

Engineer in charge

Date of issue of this English version: 15.05.2020