

50.000 N | Total Eraz Clear

Total Deco



Features

Total Eraz Clear is a high gloss polymeric PVC film used for whiteboard application. The PVC film is top coated with a low energy lacquer to ensure clean removal of the ink used in whiteboard markers. This product is typically used as an overlamine to apply over printed graphics.

The film should be applied at room temperature to achieve the best installation conditions. Apply on smooth surfaces. Please always check suitability of white board marker pen prior to installation.

50.000 N | Total Eraz Clear is available at 1350mm x 50m. All materials used to produce this

Technical & Performance Information

Film Thickness	100 microns
Adhesive Thickness	20 microns
Total Thickness	120 microns
Adhesive Type	Permanent based acrylic
Release Liner	130 gsm one side siliconised liner
Artificial weathering*	> 3 years
Film Tensile Strength MD	> 15 N/mm ²
Film Elongation MD	> 80%
Opacity	96% minimum
Adhesion to steel (20 mins / 180°)	7 N/25mm
Adhesion to steel (24 hours / 180°)	18 N/25mm

* equivalent to vertical exposure in Mid-European climate

Dry wipe marker compatibility

Marker Brand	Model/MFC	< 24 hours	48 hours	1 week	3 weeks
BIC	1.4mm	5	5	5	5
Bruynzeel	Color express 8	5	5	5	5
Edding	360 - 1.5mm	5	5	5	5
BIC	0.8mm	5	5	5	5
Harrows Darts	#3800	5	5	5	5
Staedtler	Lumocolor 2mm	5	5	5	5
Stabilo	Big Point 88	5	5	5	5

Rank Scale: (1) chemical cleaner needed to remove; (2) difficult to remove; (3) leaves ghosting; (4) good wipe off; (5) excellent wipe off with dry paper towel

Warranty

iSee2 warrants our material for one (1) year from date of shipment. The shelf life of our material is dependent on storage conditions. We recommend that the end user stores the material in the original boxes (out of direct sunlight) from our factory. We also recommend to store our material at 21°C with 50% relative humidity. iSee2 only warrants our products to be free from defects in workmanship or defects in iSee2 material. We will replace or credit any material deemed defective. No acceptance or responsibility for loss, damage or expense implied or otherwise shall be assumed by the seller or manufacturer. User assumes all risk and liability in connection herewith. All data values quoted above are typical and should not be used to deem the product defective, if measured values are different.